

Comparison of Performances of Novel Titanium carbide tool Insert and Uncoated Tool in CNC Turning of HCHC D2 Steel for Minimizing Surface Roughness and Maximizing Material Removal Rate

C. Ravi Teja¹; S. Lokesh^{2*}

¹Research Scholar, Department of Mechanical Engineering, Saveetha School of Engineering, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai, Tamilnadu, India.

¹ravitejadhoni7@gmail.com

^{2*}Project Guide, Department of Mechanical Engineering, Saveetha School of Engineering, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai, Tamilnadu, India.

^{2*}lokeshs.sse@saveetha.com

Abstract

Aim:-The Present study is focused on the comparison of performances of Titanium carbide(TIC) and Uncoated carbide tool inserts with CNC turning of HCHC D2 Steel for minimizing surface roughness and maximizing material removal rate. **Materials And Methods:-** Machining of HCHC D2 steel material was compared with Titanium carbide(TIC) and Uncoated carbide tool inserts. It was divided into two groups of 27 samples each. The samples were machined with two different tool inserts one was control group and other was experimental group. **Results:-** Surface roughness was decreased and material removal rate was increased when machining was done with TIC carbide compared to HSS tool insert ($P=0.028$). **Conclusions:** It is concluded that the surface roughness was decreased and material removal rate was increased when TIC carbide tool insert was used for machining.

Key-words: CNC Turning, Novel TiC Insert, Surface Roughness (R_a), Material Removal Rate (MRR), Feed, Speed, Depth of Cut, Cutting Threading Dies, Green Manufacturing.

1. Introduction

CNC machining is a advanced manufacturing process that typically employs computerized controls and machine tools to remove layers of materials, including metals, plastics, wood, glass, foam, and composites. The present study was focused on the comparison of Titanium carbide(TIC) and uncoated tool inserts in CNC turning of HCHC D2 Steel. It is used for long run tooling applications and has the ability to wear resistance. (Kumar, Saravanan, and Patnaik 2020; Yadav and

Shrivastava 2021). The applications were cold stamping, tyre shredders, punches, slitters which are used in day-to-day life.

In 2018 (Vipin et al. 2018) the author compared the machining performances of pcd insert with pcBN insert and concluded that the material removal rate was high when pcd tool insert was used (Meshram et al. 2020). Multiple regression analysis was done to predict the model and optimal parameters were found by using the WEDM process for this paper. (“Study of Surface Modification by Electrical Discharge Machining” 2007). Powder mixed electric discharge machining (PMEDM) is the 6 process used for machining to calculate surface roughness and material removal rate.(Rout and Jena 2021) optimization of surface roughness and analyzing through taguchi and anova methods. (Biswas, Singh, and Mukherjee 2021).

Previously our team has a rich experience in working on various research projects across multiple disciplines (Sathish and Karthick 2020; Varghese, Ramesh, and Veeraiyan 2019; S. R. Samuel, Acharya, and Rao 2020; Venu, Raju, and Subramani 2019; M. S. Samuel et al. 2019; Venu, Subramani, and Raju 2019; Mehta et al. 2019; Sharma et al. 2019; Malli Sureshbabu et al. 2019; Krishnaswamy et al. 2020; Muthukrishnan et al. 2020; Gheena and Ezhilarasan 2019; Vignesh et al. 2019; Ke et al. 2019; Vijayakumar Jain et al. 2019; Jose, Ajitha, and Subbaiyan 2020). Now the growing trend in this area motivated us to pursue this project.

Currently, the research was about turning studies Of HCHC D2 steel with different turning tools is limited. Hence in this study, Comparing the HCHC D2 steel material with Titanium carbide and Uncoated ceramic tool insert is carried out (Shah et al. 2011). The parameters like speed was decreased and increased in feed resulted during a poor surface roughness and fewer material removal rate. The material removal is found high for HCHC D2 steel with Titanium carbide turning tool. Aim of the study was to compare the surface roughness with two different tools and acquire a good surface finish to decrease the machining time and increase the assembly rate and increase the productivity.

2. Material And Methods

This study was done in Saveetha Industries, Saveetha School of Engineering, Saveetha Institute of Medical and Technical Sciences, Chennai. The total number of samples were divided into two groups. One was an experimental group and the other one control group. The tool used for machining titanium carbide is an experimental group and the tool used for machining with HSS is the control group. A total number of 54 samples are required. G Power is allowed to utilize programming used to figure measurable force. 80% G power is obtained. Confidence percentage was 90% and the

enrollment ratio was 1. The HCHC D2 steel of cylindrical length is 2700*36mm. It is cut into 54 pieces of 100mm length. The rough turning of 1mm is machined in the conventional lathe machine.

Titanium carbide, (TIC) is an incredibly hard unmanageable artistic material, like tungsten carbide (Singh, Khatirkar, and Sapate 2015). It resembles dark powder with the sodium chloride gem structure. It occurs in nature as a form of a very rare mineral (Biradar and Lathkar 2014). The VOEDM identifies the major contributing factor of pulse off time for EWR (50.33%) and MRR (34.78% (Meshram et al. 2020)). The effect of these parameters has been investigated by using Response Surface Methodology (RSM) (Walia, Srivastava, and Jain 2019). Speed, feed rate and depth of cut is compared with the uncoated Carbide tool at the same parametric values in the CNC turning machine (Shirpurkar, Waghmare, and Date 2019).

It is frequently utilized in power sharp edges and boring apparatus. It is better than the more established high carbon steel instruments utilized widely and they can withstand higher temperatures without losing their hardness. Material Removal Rate It is defined as the ratio of difference in weights before and after machining to time taken for machining. $MRR = \frac{\text{Weight before machining} - \text{weight after machining}}{\text{Time taken}}$ (Kumar, Saravanan, and Patnaik 2020).

A Rough turning of 1mm was done using a conventional lathe machine. CNC machining was done with TIC and HSS tool inserts with input parameters Speed Feed Depth of cut. The HCHC D2 steel was inserted in the three-jaw chuck of the CNC machine of 30mm length in chuck 70mm for smooth roughness. The parameters had changed at regular intervals for every sample like Speed, Feed rate, Depth of Cut. The tool inserts were fixed in the tool holder and changed the tool for every specimen and noted down the values and time taken for machining for the single workpiece (and Adinarayana. 2014). Time taken for machining was calculated. Significance was calculated using SPSS software. Error bar graph was plotted between material removal rate and groups.

The obtained results are subjected to normality tests such as SPSS Software and Minitab. An independent t-test is performed to compare the mean and standard errors. The independent sample t-test was done to define the groups.

3. Result

The material removal rate is increased in the HCHC D2 steel compared with the uncoated ceramic insert. Also, it increases the lifetime of the tool and gets good surface roughness. With increased feed and depth of cut, the material removal rate was high and the surface finish was

smooth. From the independent sample test, the significance values of Levene's test for equality of variance is 0.028.

Data collections of speed, feed, depth (L9 Orthogonal array table). All the values were different parameters. The tabulated values are the Titanium carbide tool insert. The input parameters speed, feed, depth of cut varies from 1310-1330rpm, 0.16-0.18mm/rev, 0.16-0.18mm respectively (Table 1). The table values shows the material removal rate of Titanium carbide and uncoated ceramic tool after calculating the weights of the workpieces. Titanium carbide has the highest material removal rate of 0.03692. Uncoated ceramic has the material removal rate of 0.13070 (Table 2). Represents the means and standard deviation of material removal rate. The mean and standard deviation of TIC and HSS is 0.0280265 0.0514726; .00738290 .03426953 (Table 3). Independent sample test represents the significance and Levene's test for equality of variances and t-test for equality of means in material removal rate. The significant value is $P(p=0.028)$ for Levene's test for equality of variances (Table 4). Signal to noise ratio(S/N)ratio graph was plotted. The optimum conditions for obtaining maximum MRR is with a speed of 1310, feed 0.16, depth of cut 0.16mm (Fig 1). Represents Means of means graph is plotted for speed, feed and depth of cut (Fig 2).

Table 1 - Data collections of speed, feed, depth (L9 Orthogonal array table). All the values were different parameters. The tabulated values are the Titanium carbide tool insert. The input parameters speed, feed, depth of cut varies from 1310-1330rpm, 0.16-0.18mm/rev, 0.16-0.18mm respectively.

S.NO	Speed(rpm)	Feed(mm/rev)	Depth(mm)
1	1310	0.16	0.16
2	1310	0.17	0.17
3	1310	0.18	0.18
4	1320	0.16	0.17
5	1320	0.17	0.18
6	1320	0.18	0.16
7	1330	0.16	0.18
8	1330	0.17	0.16
9	1330	0.18	0.17

Table 2 - The table values shows the material removal rate of Titanium carbide and uncoated ceramic tool after calculating the weights of the workpieces. Titanium carbide has the highest material removal rate of 0.03692. Uncoated ceramic has the material removal rate of 0.13070.

S.NO	MRR (TIC tool insert)	MRR (Uncoated tool insert)
1	2.027310	1.128000
2	2.027450	1.133750
3	2.032040	1.131760
4	2.038000	1.145790
5	2.040000	1.124620
6	2.032940	1.147690
7	2.043660	1.138640
8	2.043910	1.158640
9	2.056920	1.182040

Table 3 - Represents the means and standard deviation of material removal rate. The mean and standard deviation of TIC and HSS is 0.0280265 0.0514726; .00738290 .03426953

Group Statistics					
	Group	N	Mean	Std. Deviation	Std. Error Mean
MRR	TIC	9	.0280265	.00738290	.00246097
	HSS	9	.0514726	.03426953	.01142318

Table 4 - Independent sample test represents the significance and Levene's test for equality of variances and t-test for equality of means in material removal rate. The significant value is $P(p=0.028)$ for Levene's test for equality of variances.

Independent Samples Test										
		Levene's Test for Equality of Variances		t-test for Equality of Means						
		F	Sig.	t	df	Sig. (2-tailed)	Mean Difference	Std. Error Difference	95% Confidence Interval of the Difference	
									Lower	Upper
MRR	Equal variances assumed	5.841	.028	-2.006	16	.042	-.02344608	.01168526	-.04821772	.00132556
	Equal variances not assumed			-2.006	8.741	.027	-.02344608	.01168526	-.04999985	.00310769

Fig. 1 - Titanium carbide tool insert (TIC)



Fig. 2 - Uncoated ceramic tool insert



Fig.3 CNC Turning Machine



Fig. 4 - Signal to noise ratio(S/n)ratio graph was plotted. The optimum conditions for obtaining maximum MRR is with a speed of 1310,feed 0.16,depth of cut 0.16mm.




Fig. 5 - Represents Means of means graph is plotted for speed ,feed and depth of cut





Fig. 6 - Barchart Comparison of mean MRR (+/-1SD) of uncoated ceramic tool and titanium carbide tool insert method. Titanium carbide method appears to produce most variable results with its standard deviation ranging from the lower 1.200000 to the upper 2.000000. Uncoated ceramic tool appears to produce consistent results with minimal standard deviation. X Axis: Uncoated ceramic tool vs Titanium carbide tool Y Axis: Mean MRR +/- 1SD.



4. Discussion

The results show that the material removal rate increases when the depth of cut is increased. Depth of cut is the main reason to increase the material removal rate. The material removal rate is increased by approximately 10% for Tic tool insert. There was a 5% error (approx) in surface roughness. It reduces the tool wear and frictional losses because of a good surface finish. Tool wear rate is low and the surface finish is good. The time taken for production has decreased and the life time of the tool has increased. The significance value was ($P=0.028$)

Various methods were used to do the surface roughness and material removal rate. Powder mixed electric discharge machining (PMEDM) is a recent outcome. The R_a and MRR are not better with this method compared with the CNC machine (Rout and Jena 2021). Optimization of CNC turning machines using taguchi analysis in the dry turning operations are not better when compared with wet turning operations (Gadekula et al. 2018). Electrical discharge machining (EDM) process was not better compared with CNC machining process (Pushyanth and Bhaskar 2018). Different suitable lubricants are used for obtaining good surface roughness (Shankar and Krishnakumar 2016).

Our institution is passionate about high quality evidence based research and has excelled in various fields (Vijayashree Priyadharsini 2019; Ezhilarasan, Apoorva, and Ashok Vardhan 2019;

Ramesh et al. 2018; Mathew et al. 2020; Sridharan et al. 2019; Pc, Marimuthu, and Devadoss 2018; Ramadurai et al. 2019). We hope this study adds to this rich legacy.

The tool wear rate is low due to hard machining of HCHC D2 Steel. When speed is increased the tool gets damaged. Poor surface finish is observed when the lubricant is not used and tool wear rate is high. In future it is used for cold stamping and die forgings, punches and slitters. Die used for forging will have a smooth surface finish which results in a good quality product.

5. Conclusion

From the above findings surface roughness was decreased and material removal rate was increased when machining of HCHC D2 Steel was done with TIC tool insert. The life time of the tool was increased. The optimum conditions for obtaining good surface finish is when speed, feed, depth of cut are 1320 rpm, 0.17mm/rev, 0.17 mm respectively.

Declarations

Conflict of interest: No conflict of interest in this manuscript.

Authors Contributions

Author CRT was involved in data collection, manuscript writing. Author SL was involved in conceptualization, data validation, and critical review of manuscript.

Acknowledgement

The authors would like to express their gratitude towards Saveetha School of Engineering, Saveetha Institute of Medical and Technical Sciences(formerly known as Saveetha University) for providing the necessary infrastructure to carry out this work successfully.

Funding: We thank the following organizations for providing financial support that enabled us to complete the study.

1. Sankar Industries, Chennai.
2. Saveetha University
3. Saveetha Institute of Medical and Technical Sciences.
4. Saveetha School of Engineering.

References

- Biradar, Shantisagar K., and Geeta S. Lathkar. 2014. "Multiobjective Optimization of End Milling HCHCr Using AlCrN PVD Coated Cutters With MOGA and RSMO." *Volume 2: Processing*. <https://doi.org/10.1115/msec2014-4185>.
- Biswas, Shatarupa, Yogesh Singh, and Manidipto Mukherjee. 2021. "A Study on Optimization Techniques of Electro Discharge Machining." *Intelligent Manufacturing*. https://doi.org/10.1007/978-3-030-50312-3_1.
- Ezhilarasan, Devaraj, Velluru S. Apoorva, and Nandhigam Ashok Vardhan. 2019. "Syzygium Cumini Extract Induced Reactive Oxygen Species-Mediated Apoptosis in Human Oral Squamous Carcinoma Cells." *Journal of Oral Pathology & Medicine: Official Publication of the International Association of Oral Pathologists and the American Academy of Oral Pathology* 48 (2): 115–21.
- Gadekula, Rajesh Kumar, Mallikarjuna Potta, Diwakar Kamisetty, Uday Kumar Yarava, Priyanka Anand, and Raja Sekhar Dondapati. 2018. "Investigation on Parametric Process Optimization of HCHCR in CNC Turning Machine Using Taguchi Technique." *Materials Today: Proceedings*. <https://doi.org/10.1016/j.matpr.2018.10.131>.
- Gheena, S., and D. Ezhilarasan. 2019. "Syringic Acid Triggers Reactive Oxygen Species-Mediated Cytotoxicity in HepG2 Cells." *Human & Experimental Toxicology* 38 (6): 694–702.
- Jose, Jerry, Ajitha, and Haripriya Subbaiyan. 2020. "Different Treatment Modalities Followed by Dental Practitioners for Ellis Class 2 Fracture – A Questionnaire-Based Survey." *The Open Dentistry Journal* 14 (1): 59–65.
- Ke, Yang, Mohammed Saleh Al Aboody, Wael Alturaiki, Suliman A. Alsagaby, Faiz Abdulaziz Alfaiz, Vishnu Priya Veeraraghavan, and Suresh Mickymaray. 2019. "Photosynthesized Gold Nanoparticles from Catharanthus Roseus Induces Caspase-Mediated Apoptosis in Cervical Cancer Cells (HeLa)." *Artificial Cells, Nanomedicine, and Biotechnology* 47 (1): 1938–46.
- Krishnaswamy, Haribabu, Sivaprakash Muthukrishnan, Sathish Thanikodi, Godwin Arockiaraj Antony, and Vijayan Venkatraman. 2020. "Investigation of Air Conditioning Temperature Variation by Modifying the Structure of Passenger Car Using Computational Fluid Dynamics." *Thermal Science* 24 (1 Part B): 495–98.
- Kumar, Sunil, I. Saravanan, and Lokeswar Patnaik. 2020. "Optimization of Surface Roughness and Material Removal Rate in Milling of AISI 1005 Carbon Steel Using Taguchi Approach." *Materials Today: Proceedings*. <https://doi.org/10.1016/j.matpr.2019.09.039>.
- M. Adinarayana, and M. Adinarayana . 2014. "Parametric Analysis and Multi Objective Optimization of Cutting Parameters in Turning Operation of AISI 4340 Alloy Steel with CVD Cutting Tool." *International Journal of Research in Engineering and Technology*. <https://doi.org/10.15623/ijret.2014.0302079>.
- Malli Sureshbabu, Nivedhitha, Kathiravan Selvarasu, Jayanth Kumar V, Mahalakshmi Nandakumar, and Deepak Selvam. 2019. "Concentrated Growth Factors as an Ingenious Biomaterial in Regeneration of Bony Defects after Periapical Surgery: A Report of Two Cases." *Case Reports in Dentistry* 2019 (January): 7046203.
- Mathew, M. G., S. R. Samuel, A. J. Soni, and K. B. Roopa. 2020. "Evaluation of Adhesion of Streptococcus Mutans, Plaque Accumulation on Zirconia and Stainless Steel Crowns, and Surrounding Gingival Inflammation in Primary" *Clinical Oral Investigations*. <https://link.springer.com/article/10.1007/s00784-020-03204-9>.

Mehta, Meenu, Deeksha, Devesh Tewari, Gaurav Gupta, Rajendra Awasthi, Harjeet Singh, Parijat Pandey, et al. 2019. "Oligonucleotide Therapy: An Emerging Focus Area for Drug Delivery in Chronic Inflammatory Respiratory Diseases." *Chemico-Biological Interactions* 308 (August): 206–15.

Meshram, Diwesh B., Yogesh M. Puri, Vikas Gohil, and Sachin P. Ambade. 2020. "Novel Curved Trajectory Machining Using VOEDM Process – Experimental Study and Statistical Optimisation Thereof." *Advances in Materials and Processing Technologies*. <https://doi.org/10.1080/2374068x.2020.1793271>.

Muthukrishnan, Sivaprakash, Haribabu Krishnaswamy, Sathish Thanikodi, Dinesh Sundaresan, and Vijayan Venkatraman. 2020. "Support Vector Machine for Modelling and Simulation of Heat Exchangers." *Thermal Science* 24 (1 Part B): 499–503.

Pc, J., T. Marimuthu, and P. Devadoss. 2018. "Prevalence and Measurement of Anterior Loop of the Mandibular Canal Using CBCT: A Cross Sectional Study." *Clinical Implant Dentistry and Related Research*. <https://europepmc.org/article/med/29624863>.

Pushyanth, V. R. S., and A. Bhaskar. 2018. "Experimental Investigation and Improvement of Surface Finish Analysis on HCHCR AISI-D7 Using EDM." *Materials Today: Proceedings*. <https://doi.org/10.1016/j.matpr.2018.02.189>.

Ramadurai, Neeraja, Deepa Gurunathan, A. Victor Samuel, Emg Subramanian, and Steven J. L. Rodrigues. 2019. "Effectiveness of 2% Articaine as an Anesthetic Agent in Children: Randomized Controlled Trial." *Clinical Oral Investigations* 23 (9): 3543–50.

Ramesh, Asha, Sheeja Varghese, Nadathur D. Jayakumar, and Sankari Malaiappan. 2018. "Comparative Estimation of Sulfiredoxin Levels between Chronic Periodontitis and Healthy Patients - A Case-Control Study." *Journal of Periodontology* 89 (10): 1241–48.

Rout, Pradipta Kumar, and Pankaj Charan Jena. 2021. "A Review of Current Researches on Powder Mixed Electrical Discharge Machining (PMEDM) Technology." *Lecture Notes in Mechanical Engineering*. https://doi.org/10.1007/978-981-15-7779-6_43.

Samuel, Melvin S., Jayanta Bhattacharya, Sankalp Raj, Needhidasan Santhanam, Hemant Singh, and N. D. Pradeep Singh. 2019. "Efficient Removal of Chromium(VI) from Aqueous Solution Using Chitosan Grafted Graphene Oxide (CS-GO) Nanocomposite." *International Journal of Biological Macromolecules* 121 (January): 285–92.

Samuel, Srinivasan Raj, Shashidhar Acharya, and Jeevika Chandrasekar Rao. 2020. "School Interventions-Based Prevention of Early-Childhood Caries among 3-5-Year-Old Children from Very Low Socioeconomic Status: Two-Year Randomized Trial." *Journal of Public Health Dentistry* 80 (1): 51–60.

Sathish, T., and S. Karthick. 2020. "Wear Behaviour Analysis on Aluminium Alloy 7050 with Reinforced SiC through Taguchi Approach." *Journal of Japan Research Institute for Advanced Copper-Base Materials and Technologies* 9 (3): 3481–87.

Shah, Rutvik A., P. G. Student, M. E (Production) LDRP-ITR, Gandhinagar, Gujarat, and Ankit Darji. 2011. "A Review-An Experimental Effect of Electrode Material on MRR, Kerf Width and Surface Roughness of AISI D2 Tool Steel in WEDM." *Indian Journal of Applied Research*. <https://doi.org/10.15373/2249555x/dec2013/62>.

Shankar, S., and P. Krishnakumar. 2016. "Frictional Characteristics of PVD Coated Mechanical Seals against Carbon under Various Classes of Liquid Lubricants." *Industrial Lubrication and Tribology*. <https://doi.org/10.1108/ilt-04-2015-0046>.

- Sharma, Parvarish, Meenu Mehta, Daljeet Singh Dhanjal, Simran Kaur, Gaurav Gupta, Harjeet Singh, Lakshmi Thangavelu, et al. 2019. "Emerging Trends in the Novel Drug Delivery Approaches for the Treatment of Lung Cancer." *Chemico-Biological Interactions* 309 (August): 108720.
- Shirpurkar, Prafull P., Subhash Namdeo Waghmare, and Praful T. Date. 2019. *Optimization of Turning Process: Optimization of Turning Process Parameters by Using Tool Inserts*. Educreation Publishing.
- Singh, Kritika, Rajesh K. Khatirkar, and Sanjay G. Sapate. 2015. "Microstructure Evolution and Abrasive Wear Behavior of D2 Steel." *Wear*. <https://doi.org/10.1016/j.wear.2015.02.019>.
- Sridharan, Gokul, Pratibha Ramani, Sangeeta Patankar, and Rajagopalan Vijayaraghavan. 2019. "Evaluation of Salivary Metabolomics in Oral Leukoplakia and Oral Squamous Cell Carcinoma." *Journal of Oral Pathology & Medicine: Official Publication of the International Association of Oral Pathologists and the American Academy of Oral Pathology* 48 (4): 299–306.
- "Study of Surface Modification by Electrical Discharge Machining." 2007. *International Journal of Electrical Machining*. <https://doi.org/10.2526/ijem.12.9>.
- Varghese, Sheeja Saji, Asha Ramesh, and Deepak Nallaswamy Veeraiyan. 2019. "Blended Module-Based Teaching in Biostatistics and Research Methodology: A Retrospective Study with Postgraduate Dental Students." *Journal of Dental Education* 83 (4): 445–50.
- Venu, Harish, V. Dhana Raju, and Lingesan Subramani. 2019. "Combined Effect of Influence of Nano Additives, Combustion Chamber Geometry and Injection Timing in a DI Diesel Engine Fuelled with Ternary (diesel-Biodiesel-Ethanol) Blends." *Energy* 174 (May): 386–406.
- Venu, Harish, Lingesan Subramani, and V. Dhana Raju. 2019. "Emission Reduction in a DI Diesel Engine Using Exhaust Gas Recirculation (EGR) of Palm Biodiesel Blended with TiO₂ Nano Additives." *Renewable Energy* 140 (September): 245–63.
- Vignesh, R., Ditto Sharmin, C. Vishnu Rekha, Sankar Annamalai, and Parisa Norouzi Baghkomeh. 2019. "Management of Complicated Crown-Root Fracture by Extra-Oral Fragment Reattachment and Intentional Reimplantation with 2 Years Review." *Contemporary Clinical Dentistry* 10 (2): 397–401.
- Vijayakumar Jain, S., M. R. Muthusekhar, M. F. Baig, P. Senthilnathan, S. Loganathan, P. U. Abdul Wahab, M. Madhulakshmi, and Yogaen Vohra. 2019. "Evaluation of Three-Dimensional Changes in Pharyngeal Airway Following Isolated Lefort One Osteotomy for the Correction of Vertical Maxillary Excess: A Prospective Study." *Journal of Maxillofacial and Oral Surgery* 18 (1): 139–46.
- Vijayashree Priyadharsini, Jayaseelan. 2019. "In Silico Validation of the Non-Antibiotic Drugs Acetaminophen and Ibuprofen as Antibacterial Agents against Red Complex Pathogens." *Journal of Periodontology* 90 (12): 1441–48.
- Vipin, Vipin, Suman Kant, and C. S. Jawalkar. 2018. "Parametric Modeling in Drilling of Die Steels Using Taguchi Method Based Response Surface Analysis." *Materials Today: Proceedings*. <https://doi.org/10.1016/j.matpr.2017.12.023>.
- Walia, Arminder Singh, Vineet Srivastava, and Vivek Jain. 2019. "Impact of Copper-Titanium Carbide Tooltip on Machined Surface Integrity during Electrical Discharge Machining of EN31 Steel." *Materials Research Express*. <https://doi.org/10.1088/2053-1591/ab3ac4>.
- Yadav, Anil Kumar, and Bhasker Shrivastava. 2021. "Optimization of Surface Roughness and Material Removal Rate in Turning of AISI D2 Steel with Coated Carbide Inserts." *Proceedings of International Conference on Data Science and Applications*. https://doi.org/10.1007/978-981-15-7561-7_14.